## التكسير الحفزي للملوثات العضوية باستخدام توليفات متناهية الصغرمن حبيبات هيدروجل المطعمة بالمعدن

إعداد حامد أحمد إبراهيم الشيخي

إشراف أ. د/ عبد الله محمد عسيري أ. د/ شير بهادر خان

## المستخلص

تم تعضير أكسيد السيريوم المطعم بالكوبلت (Co-CeO<sub>2</sub>) وخلطه داخل حبيبات هيدروجيل الألجينات (Alg/Co-CeO<sub>2</sub>). ثم تم غمس حبات (Alg/Co-CeO<sub>2</sub>) في محلول نحاسي حيث تمتص الحبيبات أيونات النحاس (Cu) من المحلول وتحوبلها إلى جزيئات نانوية من النحاس عن طريق المعالجة بواسطة صوديوم بيرهيدر ايد (NaBH<sub>4</sub>). ثم تم اجراء الاختبار على حبات مركب (Alg/Co-CeO<sub>2</sub>) المزينة بالنحاس (Cu@Alg/Co-CeO<sub>2</sub>) كمحفز للتحلل الضوئي بمساعدة الطاقة الضوئية، وبمساعدة مركب (NaBH<sub>4</sub>) لتساعد في تقليل الملوثات العضوية. من بين الأصباغ المختلفة، تم العثور على الضوئية، وبمساعدة مركب (Cu @ Alg / Co-CeO<sub>2</sub>) بنسبة تصل الى (ArO) تحت الضوء. بينما وجد كمحفز فعال لتقليل (MO) في وجود (NaBH<sub>4</sub>). تم إزالة لون صبغة (ArO) بنسبة تصل الى ۷۰٪ خلال خمس ساعات تحت الضوء. بينما

## Catalytic Degradation of Organic Pollutants using Metal Decorated Hydrogel Beads Nanocomposite

By Hamed Ahmed Alshaikhi

Supervised By Prof. Dr. Abdullah Mohamed Asiri Prof. Dr. Sher Bahadar Khan

## **Abstract**

Cobalt doped cerium oxide (Co-CeO<sub>2</sub>) was prepared and wrapped inside the alginate (Alg) hydrogel beads. Alg/Co-CeO<sub>2</sub> beads were further dipped in copper solution where the beads adsorbed Cu ions from solution and converted into Cu nanoparticles by treating with sodium borohydride (NaBH<sub>4</sub>). Cu decorated Alg/Co-CeO<sub>2</sub> composite beads (Cu@Alg/Co-CeO<sub>2</sub>) were tested as a catalyst for the solar assisted photodegradation and NaBH<sub>4</sub> assisted reduction of organic pollutants. Among different dyes, Cu@Alg/Co-CeO<sub>2</sub> was found best catalyst for the photodegradation of ArO under solar light while efficient catalyst for reduction of MO in the presence of NaBH<sub>4</sub>. Cu@Alg/Co-CeO<sub>2</sub> decolorized ArO up to 75% in 5 hr under solar light while 97% of MO was reduced in 11 min in the presence of NaBH<sub>4</sub>. The decolorization efficiency of Cu@Alg/Co-CeO<sub>2</sub> was further optimized by varying different parameters.